

**Technical Data Sheet**

Page 1 of 1

<b>Properties:</b>	AKEMI® Super Glue Activator increases the curing speed of cyanoacrylate adhesives.  The product is characterized by the following qualities: <ul style="list-style-type: none"><li>- 2 in 1 product cleans, degreases and speeds up curing time</li><li>- the application can be either pre- or post-applied to the bond</li><li>- significantly improves the fixture time</li><li>- can be used for almost all materials incl. plastic</li></ul>																
<b>Application Area:</b>	AKEMI® Super Glue Activator is used where increased curing speed is required. Typical applications include securing different materials such as glass, plastic etc. whenever a quick fix between close fitting parts is required.																
<b>Instructions for Use:</b>	<ol style="list-style-type: none"><li>1. For best results surfaces to be bonded must be clean and free from grease using AKEMI® Super Glue Activator.</li><li>2. Apply AKEMI® Super Glue Activator on one part to be assembled.</li><li>3. Apply the adhesive onto the opposite side.</li><li>4. Bring the surfaces together and apply firm pressure.</li><li>5. If necessary, spray AKEMI® Super Glue Activator onto the adhesive after bonding.</li></ol>																
<b>Special Notes:</b>	<ul style="list-style-type: none"><li>- For professional use only.</li><li>- For proper waste disposal, the container must be completely emptied.</li><li>- Recycling in accordance with the guidelines of EU Decision 97/129 EC on the Packaging Directive 94/62/EC.</li></ul>																
<b>Technical Data:</b>	<table><tr><td>Base:</td><td>organic substance in a soluble composition</td></tr><tr><td>Colour:</td><td>clear</td></tr><tr><td>Initial strength:</td><td>1 - 4 seconds, depending on adhesive gap and room temperature</td></tr><tr><td>Viscosity at 20°C:</td><td>1 - 2 mPas</td></tr><tr><td>Specific weight at 20°C:</td><td>0.8 g/ml</td></tr><tr><td>Flash point ISO 2592:</td><td>0°C</td></tr><tr><td>Vapour pressure at 25°C:</td><td>50 mbar</td></tr><tr><td>Toxicity:</td><td>TLV 270 ppm</td></tr></table>	Base:	organic substance in a soluble composition	Colour:	clear	Initial strength:	1 - 4 seconds, depending on adhesive gap and room temperature	Viscosity at 20°C:	1 - 2 mPas	Specific weight at 20°C:	0.8 g/ml	Flash point ISO 2592:	0°C	Vapour pressure at 25°C:	50 mbar	Toxicity:	TLV 270 ppm
Base:	organic substance in a soluble composition																
Colour:	clear																
Initial strength:	1 - 4 seconds, depending on adhesive gap and room temperature																
Viscosity at 20°C:	1 - 2 mPas																
Specific weight at 20°C:	0.8 g/ml																
Flash point ISO 2592:	0°C																
Vapour pressure at 25°C:	50 mbar																
Toxicity:	TLV 270 ppm																
<b>Storage:</b>	If stored in dry and cool condition (5-25°C/41-77°F) in its closed original container at least 5 years from production.																
<b>Health &amp; Safety:</b>	Read Safety Data Sheet before handling or using this product.																
<b>Important Notice:</b>	The above information is based on the latest stage of development and application technology. Due to a multiplicity of different influencing factors, this information – as well as other oral or written technical advises – must be considered as non-binding hints. The user is obliged in each particular case to conduct performance tests, including but not limited to trails of the product, in an inconspicuous area or fabrication of a sample piece.																

TDS 02.26