

**Technical Data Sheet**

Page 1 of 2

<b>Properties:</b>	<p>AKEMI® Wheel Rim Clear is a high-quality 1-component clearcoat containing solvents.</p> <p>The product is characterized by the following properties:</p> <ul style="list-style-type: none"><li>- fast drying</li><li>- very good adhesion on metal (iron, nickel, aluminium, tin, brass, chromium, copper, silver), cardboard and wood</li><li>- weather-resistant, does not yellow</li><li>- gloss-resistant, lightproof</li><li>- conditionally stable towards petrol, resistant to thawing salt and car wash</li></ul>								
<b>Application Area:</b>	<p>AKEMI® Wheel Rim Clear seals alloy rims and thus facilitates their cleaning and protects against stubborn staining. The product is also used as a protection film for painted steel rims (AKEMI® Wheel Rim Gold/Silver/White). The product can also be used in the domestic sector and for hobby purposes.</p>								
<b>Instructions for Use:</b>	<ol style="list-style-type: none"><li>1. The surface must be free of rust and grease, thoroughly clean, dry and slightly roughened.</li><li>2. Shake the spray can vigorously before use (you can hear the mixing balls).</li><li>3. Cover up parts which are not to be sprayed.</li><li>4. Apply several thin layers (at a spraying distance of approx. 25 cm and at intervals of 3 - 5 minutes).</li></ol>								
<b>Special Notes:</b>	<ul style="list-style-type: none"><li>- For professional use only.</li><li>- Do not use at too high temperatures or in intense sunlight as the paint dries too quickly and does not run properly (blooming). Optimum working temperature 15 - 25°C.</li><li>- Drying is far better if the product is applied in several thin layers instead of one thick one.</li><li>- It is not necessary to empty the spray nozzle when you have finished your work.</li><li>- Areas which have accidentally been sprayed can be cleaned with AKEMI® Universal Thinner (check the compatibility).</li><li>- Only limited resistance to petrol.</li><li>- For proper waste disposal, the container must be completely emptied.</li><li>- Recycling in accordance with the guidelines of EU Decision 97/129 EC on the Packaging Directive 94/62/EC.</li></ul>								
<b>Technical Data:</b>	<table><tr><td>Colour:</td><td>colourless shiny</td></tr><tr><td>Density:</td><td>approx. 0.8 g/cm<sup>3</sup></td></tr><tr><td>Drying:</td><td>dust-dry after approx. 10 min touch-dry after approx. 60 min completely dry after approx. 24 h</td></tr><tr><td>Coverage:</td><td>approx. 1 - 2 m<sup>2</sup>/spray can</td></tr></table>	Colour:	colourless shiny	Density:	approx. 0.8 g/cm <sup>3</sup>	Drying:	dust-dry after approx. 10 min touch-dry after approx. 60 min completely dry after approx. 24 h	Coverage:	approx. 1 - 2 m <sup>2</sup> /spray can
Colour:	colourless shiny								
Density:	approx. 0.8 g/cm <sup>3</sup>								
Drying:	dust-dry after approx. 10 min touch-dry after approx. 60 min completely dry after approx. 24 h								
Coverage:	approx. 1 - 2 m <sup>2</sup> /spray can								
<b>Storage:</b>	<p>If stored in dry and cool condition (5-25°C/41-77°F) in its closed original container at least 5 years from production.</p>								
<b>Health &amp; Safety:</b>	<p>Read Safety Data Sheet before handling or using this product.</p>								

TDS 09.25

**Technical Data Sheet**

Page 2 of 2

**Important Notice:**

The above information is based on the latest stage of development and application technology. Due to a multiplicity of different influencing factors, this information – as well as other oral or written technical advises – must be considered as non-binding hints. The user is obliged in each particular case to conduct performance tests, including but not limited to trails of the product, in an inconspicuous area or fabrication of a sample piece.