

Technical Data Sheet

Page 1 of 2

- Properties:** AKEMI® Filler Super Soft is a 2-component filler based on unsaturated polyester resins dissolved in styrene.
- The product is characterized by the following qualities:
- good drawing properties due to especially creamy consistency
 - high filling and non-sag properties
 - levelling of slightly scratches and uneven surfaces due to especially fine structure
 - fast hardening (10 - 15 minutes)
 - easy sanding and high abrasion
 - very good adhesion on metal (iron, steel, aluminum), wood, stone and various plastics (e.g. rigid PVC, polyester) also in case of higher temperatures (up to 100°C)
 - resistant to water, petrol, mineral oils, diluted lye and acids
- Application Area:** AKEMI® Filler Super Soft is mainly used in body shops, commercial vehicle construction or in the engineering industry for levelling of dents, uneven surfaces, scratches or shrink holes. Additionally, the product can be used in model construction or other hobbies as well as for bonding of parts made of above-mentioned materials which are not exposed to high mechanical stress.
- Instructions for Use:**
1. The surface to be treated must be free of rust and dust, dry and slightly roughened. Uncured old paint or thermoplastic acrylic paint must be removed.
 2. Add 1 to 4 g of red hardener paste to 100 g of filler (4 to 5 cm of paste pressed out of the screw tube correspond to 1 g).
 3. Both components are mixed until a homogeneous shade of colour is achieved. The mixture can be worked for about 2 to 8 minutes.
 4. After 15 to 30 minutes the hardened filler can be worked (ground, drilled, milled).
 5. The hardening process is accelerated by heat and delayed by cold.
 6. The finished filler surface can be reworked with all commercially available fillers and paints.
 7. Tools can be cleaned with AKEMI® Nitro-Thinner.
- Special Notes:**
- For professional use only.
 - In case of metallic surfaces, fillers should be applied as soon as possible after sanding to avoid a reduction in adhesion.
 - Hardener portions higher than 4% reduce adhesion and deteriorate surface drying.
 - Hardener portions less than 1% delay hardening or low temperatures cause an incomplete hardening and the surface will remain tacky.
 - Before coating with a 2C acrylic paint, apply a primer or a „Non-Sanding Sealer to avoid blistering.
 - If the product is to be applied in thicker layers, work with as little hardener as possible or in several layers
 - Once hardened, the filler can no longer be removed by solvents. Removal is only possible mechanically or by higher temperatures (> 200°C).
 - Being worked properly, the hardened filler is harmful to health.
 - For proper waste disposal the container must be completely emptied.
 - Recycling in accordance with the guidelines of EU Decision 97/129 EC on the Packaging Directive 94/62/EC.

TDS 01.23

Technical Data Sheet

Page 2 of 2

Technical Data:	Colour:	light grey
	Density:	approx. 1.98 g/cm ³
	Working time / min.:	
	a) at 20°C	
	1% of hardener:	8 - 10
	2% of hardener:	4 - 5
	3% of hardener:	3 - 4
	4% of hardener:	2 - 3
	b) with 2% of hardener	
	at 10°C:	9 - 11
	at 20°C:	4 - 5
	at 30°C:	2 - 3
Storage:	If stored in dry and cool condition (5-25°C/41-77°F) in its closed original container at least 12 months from production.	
Health & Safety:	Read Safety Data Sheet before handling or using this product.	
Important Notice:	The above information is based on the latest stage of development and application technology. Due to a multiplicity of different influencing factors, this information – as well as other oral or written technical advises – must be considered as non-binding hints. The user is obliged in each particular case to conduct performance tests, including but not limited to trials of the product, in an inconspicuous area or fabrication of a sample piece.	

TDS 01.23